



Mobilux™ XP 222

Mobil Industrial , Argentina

Mobil Grease, General Purpose Antifriction Grease.

Product Description

Mobilux™ XP 222 is a high performance lithium hydroxystearate grease formulated to help in reducing friction between parts in movement and last longer when compared with conventional greases. It also provides extra protection against wear, rusting and water washout. Mobilux XP 222 is a NLGI 2 grease and is blended with an ISO VG 460 viscosity oil.

Mobilux XP 222 is recommended for a wide range of industrial applications including heavy-duty applications where high shock loads are present. This grease is suitable for equipment where moist or wet conditions are common based on its excellent protection against rust and corrosion and resistance to water wash-out. Mobilux XP 222 is a general-purpose grease. The recommended operating temperature range is from -20°C to 120°C but they may be used at higher temperatures if the lubrication frequency is increased accordingly.

Features and Benefits

Mobilux XP 222 provides good performance in the areas of friction and corrosion protection and long service life. It also provides good load carrying and extreme pressure.

Mobilux XP 222 uses specially selected additives to provide excellent rust and corrosion control, resistance to water contamination as well as anti-wear and EP protection. Mobilux XP 222 grease offers the following features and potential benefits:

Features	Advantages and Potential Benefits
Improved protection against wear under heavy or shock loading and vibration	Protection against rust and corrosion and good lubrication even in presence of water
Resistance to water washout	Protection against rust and corrosion and good lubrication even in presence of water
Improved anti wear and extreme pressure capabilities	Extended bearing life for reduced maintenance costs and unplanned downtime

Applications

Mobilux XP 222 can be used in mechanical components installed in industrial, automotive, construction and marine applications such as plan and rolling bearings, bushings, chains, screws, etc. The light brown color of Mobilux XP 222 enables easy verification of application. This grease is blended with an ISO VG 220 base oil viscosity and can be used in a wide range of medium to high load applications at slow-to-moderate speeds, including most bearing applications in the paper, construction, and mining industries, as well as off-highway vehicles.

Properties and Specifications

Property	
Grade	NLGI 2
Color, Visual	Light Brown

Property	
Four-Ball Wear Test, Scar Diameter, mm, ASTM D2266	0.42
Dropping Point, °C, ASTM D2265	259
Water Washout, Loss @ 79 C, wt%, ASTM D1264	5.7
Roll Stability, Penetration Consistency Change, 0.1 mm, ASTM D1831	9.4
Water Resistance, 3 h @ 90 C, Rating, DIN 51807-1	0
Penetration, 60X, 0.1 mm, ASTM D217	265
Four-Ball Extreme Pressure Test, Weld Point, kgf, ASTM D2596	250
Oxidation Stability, Pressure Drop, 100 h, kPa, ASTM D942	21
Base Oil Viscosity of Greases @ 40 C, mm ² /s, AMS 1697	220

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

03-2024

Cosan Lubricantes S.R.L.

Av. Libertador 6343, Piso 8

CABA, CP 1498, Buenos Aires – Argentina

0800 345 79540

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

ExxonMobil



© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved