



## WAXREX™1281

ExxonMobil Specialties , Canada

### Product Description

Waxrex 1281 is a lower-range melting point semi-refined paraffin wax. It is derived from petroleum via a carefully controlled refining process to provide low color and controlled oil content. Waxrex 1281 meets the requirements for most industrial wax applications and Food and Drug Administration (FDA) standards for indirect food contact substances. Waxrex 1281 is a translucent crystalline material in the solid state and is water-white in color and low in viscosity when molten. It is composed mainly of normal, straight chain paraffin hydrocarbons that impart properties of water repellency.

Waxrex 1281 contains an oxidation inhibitor to enhance the natural resistance to oxidation.

ExxonMobil waxes are produced and controlled according to the ExxonMobil Product Quality Management System, EN ISO 9000 or equivalent standard.

### Applications

Waxrex 1281 is primarily used as a component in the manufacture of candles subject to applicable laws and regulations in each jurisdiction\*.

\* User must check compliance with applicable regulations.

### Properties and Specifications

Property	Standard Method(a)	Typical	Min	Max
Melting Point, °C (F)	ASTM D87		51.0 (123.8)	56.0 (132.8)
Oil Content, wt%	ASTM D721		0	5.0
ASTM Saybolt D156 Color (ASTM D6045 Acceptable)	ASTM D6045		28	
Odor, Wax	ASTM D1833			1
Kinematic Viscosity @ 100 C, mm <sup>2</sup> /s	ASTM D445	3.7		
Density @ 15 C, kg/m <sup>3</sup>	ASTM D1298	820		
Flash Point, Cleveland Open Cup, °C (F)	ASTM D92		204(400)	
Needle Penetration, 25 C, 0.1 mm	ASTM D1321	39		

Note 1: Products are certified on release to meet the values specified. Actual values may deviate within the established reproducibility of the test method specified.

Note 2: For purpose of determining conformance with specification, observed or calculated values shall be rounded off to the nearest unit in the last significant digit used in expressing the limiting value in accordance to the ASTM E 29 method

(a) Results referenced against standard method shown. Alternate methods may be used to certify value.

(b) Density at 15°C is based on measurement of the wax liquid density at a higher temperature corrected to 15°C using ASTM D1250 Table B.

### Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

11-2020

Imperial Oil

Petroleum and Chemicals Division  
Lubricants and Specialties  
240 Fourth Ave SW  
C. P. 2480, Station M  
Calgary AB T2P 3 M 9

1-800-268-3183

The information contained herein is subject to change without notice. Every care has been taken in the preparation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same. All products may not be available locally. For more information, contact your local Imperial Oil contact or visit [www.imperialoil.ca](http://www.imperialoil.ca).

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

Energy lives here™

**ExxonMobil**

Exxon Mobil  

© Copyright 2003-2019 Exxon Mobil Corporation. All Rights Reserved