



MOBILCUT 260-NEW

Mobil Industrial , France

Aqueous Metal Working Fluid

Product Description

Mobilcut is the trademark for Mobil Industrial lubricants line of high performance water miscible metalworking fluids. All Mobilcut products are free of chlorinated and formaldehyde release agents (FAD).

Mobilcut 260-New is a high performance fluid that readily emulsifies in water to form a stable milky emulsion. The product is design for a wide range of water qualities especially for harder waters and it has good resistance to foaming for softer water, even in high pressure systems.

Although containing only very little amount of stabilizers, it is extremely tolerant against dirt and contamination and therefore offers extended coolant life relative to conventional soluble oils while easy to care and maintain. Mobilcut 260-New is free of boron.

It offers an outstanding and sustainable corrosion protection and very good wetting and detergency properties. Its base oil selection together with EP additives and lubricity agents offers a high degree of machining performance and very high output quality for aluminium and its alloys.

Mobilcut 260-New is proved to have no particular dermatological relevance.

Features and Benefits

Mobilcut 260-New water miscible cutting fluid is designed to help increase the productivity of modern machine shops by providing high performance features.

| Features | Advantages and Potential Benefits |
|--|--|
| Suitable for a variety of materials including Aluminium and Copper Alloys and Aluminium. | No stain on finished pieces |
| Wide range of machining applications | Potential to consolidate products and reduce inventories |
| High degree of corrosion protection | Reduces machine maintenance and rework of materials |
| Extremely tolerant against dirt and contaminations | Ease of use and maintenance, less risk for unpleasant odors, longer fluid life |

Applications

Mobilcut 260-New especially enhances performance when machining aluminum and aluminum alloys and where low staining potential is important on sensitive components.

Mobilcut 260-New is suitable for the machining of steel and copper alloys as well. During the machining of copper alloys, the color of the emulsion might turn into green however there will be no staining on work pieces.

Minimum concentration should be 6%. On difficult applications or materials the concentration can be increased up to 8-12%.

Water hardness ideally should range from 15° dH up to 25°dH. On the run the emulsion is stable with a water hardness up to 60°dH. Fluid type is milky emulsion. Mineral oil content is typically 45%. Its refractometer factor is 1.0.

Recommended concentrations for typical operations:

Low alloy steels - milling, turning: 6-9%

Carbon alloy steels, difficult machining: 8-12%

Aluminum, Aluminium machining: 8-12%

Properties and Specifications

| Property | |
|--|--------------------------|
| Appearance, AA.Lab.101 | Yellowish, slightly hazy |
| Appearance, 5.0% in 20 deg dH Water, AA.Lab.101 | Milky |
| Kinematic Viscosity @ 20 C, mm ² /s, ASTM D7042 | 190 |
| Density 15 C, kg/m ³ , DIN EN ISO12185 | 957 |
| pH-Value 5.0% in 20 deg dH Water, DIN 51369 | 9.9 |

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

05-2020

ESSO Société Anonyme Française

Tour Manhattan

La Défense 2

5/6 Place de l'Iris

92400 Courbevoie

FRANCE

You can always contact our Technical Help Desk engineers on Mobil lubricants and services related questions: <https://www.mobil.fr/fr-fr/contact-us>

+33 (0)1.57.00.70.00

<http://www.exxonmobil.com>

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

Energy lives here™

ExxonMobil

Exxon

Mobil

Esso

XTO
21C 82 V

© Copyright 2003-2019 Exxon Mobil Corporation. All Rights Reserved