



Wyrol™

Mobil Industrial , Greece

Roll Oil Additive Concentrate for Aluminium Rolling Mills

Product Description

Wyrol™ products are a comprehensive range of liquid additive concentrates for optimising the frictional characteristics of cold rolling oils such as the Somentor . They are designed and made available to allow aluminium rolling mills to optimise performance from the mill and achieve the required surface finish and quality substrate.

Wyrol 2 is an oxidation inhibitor concentrate that is used to extend the life of the roll oil

Wyrol 4 and 8 are each comprised of a single lubricity additive, together with a small amount of anti-oxidant. These products are used to optimise the proper aluminium roll oils in terms of their frictional characteristics. They also enable the mill operator the opportunity to optimise the formulation to suit the conditions pre on a specific mill.

Wyrol 10, 12 and 15 consist of a combination of different lubricity additives, which together with an oxidation inhibitor, help provide excellent frictional characteris a range of cold rolling oils under different conditions.

Wyrol 2, 4, 6, 8, 10 and 12 are designed to be in compliance with FDA 21 CFR 178.3910(a), "Surface Lubricants used in the manufacture of metallic articles", and ar for rolling of foil or sheet stock for food applications.

Features and Benefits

Wyrol products offer the following benefits:

Wyrol products provide a high degree of flexibility for the customer to fine-tune roll oils to obtain the optimum performance from their roll oils and the mills. This le increased production of acceptable quality material and reduces the potential for reject material.

- Optimised mill production and quality of finished product
- Can significantly extend roll oil life
- Improved finished product quality
- Reduced reject and waste production material

Applications

For optimum performance we recommend to have the product stored in a warmer (30°C) environment for 24 h prior use, this is especially valid if the product ha stored in a temperature below 5 °C for a longer time (several months).

Specifications and Approvals

This product meets or exceeds the requirements of:	10	12	2	4	6	15
FDA 21 CFR 178.3910(a)	X	X	X	X	X	X

Properties and Specifications

Property	2	4	6	8	10	12
Appearance, AMS 1738	Clear and Bright	Clear and Bright	Clear and Bright	Clear and Bright	Clear and Bright	Clear and f

Property	2	4	6	8	10	12
Ash, mass%, ASTM D482	<0.005	<0.005	<0.005	<0.005	<0.005	<0.005
Density @ 15 C, kg/m3, ASTM D4052	830	795	858	830	840	
Flash Point, Pensky-Martens Closed Cup, °C, ASTM D93	93	93	111	110	80	105
Kinematic Viscosity @ 40 C, mm2/s, ASTM D445	2.2					
Neutralization Number, mgKOH/g, ASTM D974	<0.3	55	<0.2		<0.5	<0.1
Pour Point, °C, ASTM D97		24	-3	18	6	18

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>
All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

04-2024
ExxonMobil Lubricants & Specialties

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All properties may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com
ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entity.

ExxonMobil

Exxon

Mobil

Esso

XTO

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved