# Mobil

## Mobil Centaur XHP 460 Series

Mobil Grease , Japan Multipurpose Calcium Sulphonate Complex Grease

#### Product Description

Mobil Centaur XHP 460 Series greases are a premium family of greases formulated with advanced calcium sulfonate thickener technology. The calcium sul thickener carries both inherent rust protection and extreme pressure(EP) properties. Compared to conventional soap-base thickeners (i.e. lithium, aluminum, c soaps), the calcium sulfonate thickener used in Mobil Centaur XHP 460 Series excels in water saturated environments, providing rust protection between re-lubrication intervals. The inherent EP properties exhibit great stability in the presence of water, allowing a balance between wear protection and resista corrosion.

Mobil Centaur XHP 460 Series greases are particularly well suited to meet the demanding lubrication requirements of steel mill and paper machine equipment. Centaur XHP 460 Series greases provide a balanced combination of water washout and water spray-off resistance, as well as excellent corrosion protection, ir severely wet environments. The calcium sulfonate thickeners used are also able to maintain their consistency and EP protection characteristics even with high le water contamination.

#### Features and Benefits

Mobil Centaur XHP 460 Series greases are members of the Mobil brand of lubricating products recognized for their high quality and reliability, as well as perfor capabilities. This family of products is manufactured to the strictest quality standards. A key feature for this product family is its reputation for reliability and consi: as well as its ability to handle tough applications. Mobil Centaur XHP 460 Series greases are formulated with high-performance calcium sulfonate thickener tech and are specifically designed for steel and papermill applications. Mobil Centaur XHP 460 Series greases offer the following benefits:

- · Excellent extreme-pressure protection and load-carrying ability for equipment protection under heavy and shock loading
- Excellent high temperature oil bleed control
- Reliable bearing lubrication for operations up to 232 C (450 F) with proper re-greasing intervals
- An advanced polymer additive package which resists water washout
- Ability to absorb free water, without losing thickener consistency
- Extended re-grease intervals, reducing grease consumption

#### Applications

Mobil Centaur XHP 460 Series greases are recommended for heavily loaded and water saturated applications in the steel and paper mill environments. Specific exa of such applications include:

- Ladle turret bearings
- Continuous casters
- Hot rolling work roll bearings
- Roll necks
- Couch, press and breast rolls
- Wood pellet mill roll bearings

#### Specifications and Approvals

This product meets or exceeds the requirements of:	461
DIN 51825:2004-06 - KPF 1 K -20	x

### Mobil Centaur XHP 460 Series

Property	461	462
Grade	NLGI 1	NLGI 2
Thickener Type	Calcium Sulfonate	Calcium Sulfonate
Color, Visual	BROWN	BROWN
Dropping Point, °C, ASTM D2265	275	275
Four-Ball Extreme Pressure Test, Weld Point, kgf, ASTM D2596	400	400
Four-Ball Wear Test, Scar Diameter, mm, ASTM D2266	0.6	0.6
Penetration, 60X, 0.1 mm, ASTM D217	315	280
Viscosity @ 100 C, Base Oil, mm2/s, ASTM D445	30.8	30.8
Viscosity @ 40 C, Base Oil, mm2/s, ASTM D445	460	460
Viscosity Index, ASTM D2270	96	96
Water Sprayoff, Loss, %, ASTM D4049	25	20
Water Washout, Loss @ 79 C, wt%, ASTM D1264	1.0	0.5

#### Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

01-2023 ExxonMobil Japan Godo Kaisha Shinagawa Grand Central Tower 2-16-4, Konan, Minato-Ku, Tokyo, 108-8218,

Japan

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All primary not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

