



Mobil SHC™ Grease 681 WT

Mobil Grease , South Korea

High Performance Synthetic Grease for Wind Turbines

Product Description

Mobil SHC™ Grease 681 WT is specially formulated to lubricate yaw, pitch and main bearings of wind turbines. It is a high performance synthetic lithium complex specially designed to exceed the demanding requirements of wind turbine applications at extreme temperatures. The advanced synthetic base fluid with its low tr coefficient provides excellent low temperature pumpability and very low starting and running torque.

Features and Benefits

- Superb thermal stability and oxidation resistance compared to conventional greases helps provide extended service life with longer relubrication intervals for turbines
- Outstanding low temperature performance compared to conventional greases provides excellent protection at low temperatures providing low torque on start-up at low temperatures
- Excellent rust and corrosion protection provides enhanced performance in wet conditions for reduced downtime and maintenance costs compared to conventional greases
- Outstanding structural stability in the presence of water helps retain grease consistency in hostile aqueous environments
- Excellent low temperature pumpability provides reliable lubrication of bearings using centralized grease systems or grease dispensers.
- Low traction base oil coefficient offers potential improved mechanical life and reduced energy costs versus conventional greases.
- Increased oil viscosity for extra protection with excellent low temperature properties
- No dye for improved housekeeping
- Excellent performance in the Wind Industry Riffel test

Applications

- Mobil SHC Grease 681 WT is an NLGI 1.5 Grade extreme pressure grease with ISO VG 680 synthetic base fluid recommended for tough wind turbine applications requiring additional EHL protection
- Mobil SHC Grease 681 WT meets most specifications of wind turbine builders and component suppliers and can demonstrate outstanding performance lubrication of yaw, pitch, and generator bearings either manually greased or using centralized grease systems or grease dispensers.
- Recommended application temperature range for continuous operation is from -40° C to 150°C with proper regreasing intervals

Typical Properties

| | Mobil SHC Grease 681 WT |
|--|-------------------------|
| NLGI Grade | 1.5 |
| Thickener Type | Lithium Complex |
| Colour, Visual | Beige |
| Penetration, Worked, 25°C, ASTM D 217 | 305 |
| Dropping Point, °C, ASTM D 2265 | 260 |
| Viscosity of Oil, ASTM D 445, cSt 40°C | 680 |
| Viscosity of Oil, ASTM D 445, cSt 100°C | 74 |
| Roll Stability, Pen Change, ASTM D 1831, mm/10 | 10 |
| 4-Ball Wear Scar, ASTM D 2266 | 0.6 |
| 4-Ball Weld, ASTM D 2596, Load, Kg | 250 |
| Water Washout, ASTM D 1264, Loss at 79°C. % wt | 7 |
| EMCOR Rust Test, 10 % Synthetic Sea Water, ASTM 6138 | 0,0 |

| | Mobil SHC Grease 681 WT |
|---|-------------------------|
| Corrosion Protection, ASTM D 1743, Rating | Pass |
| Copper Strip Corrosion, ASTM D 4048, Rating | 1a |

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

06-2023

Mobil Korea Lube Oil Inc.

Level 22, Seoul Square bd., Hangang-daero, Jung-gu, Seoul, Korea

+82-2-750-8700

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product perfor are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All pr may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is inten override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

ExxonMobil

Exxon

Mobil

Esso

XTL

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved