



Mobil 1™ Synthetic Grease

Mobil Grease , United States

High performance automotive grease

Product Description

Mobil 1™ Synthetic Grease, the official automotive grease of NASCAR, is an advanced full synthetic grease formulated with a proprietary blend of high-perfor synthetic base stocks and a lithium complex soap thickener. The thickener system provides a high dropping point, while additives impart excellent extreme-pr properties and resistance to water wash, rust and corrosion. The proprietary blend of high-performance synthetic base stocks used in Mobil 1 Synthetic Grease reliable lubrication over wide temperature ranges -50 C (-58 F) to 246 C (475 F). Outstanding structural stability coupled with high performance synthetic base make Mobil 1 Synthetic Grease an outstanding all-purpose automotive grease.

Features and Benefits

Features	Advantages and Potential Benefits
All-Purpose Automotive Grease	<ul style="list-style-type: none">Reliable lubrication over wide temperature range -50 C (-58 F) to 246 C (475 F)75 % reduction in torque need at -40 F (-40 C) ¹
Wide Operating Temperature Range	-40C (-40F) to 150C (302 F)
Excellent Resistance to Rust and Corrosion	<ul style="list-style-type: none">Longer life of bearings and chassis lube points when exposed to corrosive environments
Outstanding Structural Stability	<ul style="list-style-type: none">Provides effective lubrication over extended periods of time
Exceptional wear protection under heavy loads	<ul style="list-style-type: none">20 % Improved wear protection ².Provides bearing protection while cornering and other conditions where bearings temporarily experience l loads.
Excellent resistance to water wash	<ul style="list-style-type: none">40% better resistance to water wash out³ from heavy rain storms or exposure to high amounts of water.
Improved grease bearing life	<ul style="list-style-type: none">3X improvement in grease bearing life⁴

Disclaimers:

¹Based on ASTM D4693 vs mineral oil grease

²Based on ASTM D2266 vs mineral oil grease

³Based on ASTM D1264 vs mineral oil grease

⁴Based on DIN 51821 vs mineral oil grease

NASCAR® is a registered trademark of the National Association for Stock Car Auto Racing, Inc.

Applications

Mobil 1™ Synthetic Grease meets the requirements of the National Lubricating Grease institute (NLGI) performance classification GC-LB. It is recommend automotive applications at both high and low temperatures. It is particularly suited for applications such as disc brake wheel bearings and ball and steering joints provide outstanding bearing protection under heavy loads at any highway speed, and where moisture or condensation is a factor.

Specifications and Approvals

This product meets or exceeds the requirements of:
NLGI GC-LB

Properties and Specifications

Property	
Grade	NLGI 2
Thickener Type	Lithium Complex
Four-Ball Extreme Pressure Test, Load Wear Index, kgf, ASTM D2596	51
Corrosion Preventive Properties, Rating, ASTM D1743	Pass
Oil Separation, 0.25 psi, 24 h @ 25 C, mass%, ASTM D1742	3
Penetration, 60X, 0.1 mm, ASTM D217	280
Dropping Point, °C, ASTM D2265	300
Color, Visual	Red
Viscosity @ 40 C, Base Oil, mm ² /s, ASTM D445	150
Timken OK Load, lb, ASTM D2509	60
Copper Strip Corrosion, 24 h, 100 C, Rating, ASTM D4048	1B
Four-Ball Extreme Pressure Test, Weld Point, kgf, ASTM D2596	315
Four-Ball Wear Test, Scar Diameter, mm, ASTM D2266	0.5
Water Washout, Loss @ 79 C, wt%, ASTM D1264	3
Low Temperature Torque, 60 s, -40 C, N m, ASTM D4693	1

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

05-2022

Exxon Mobil Corporation

22777 Springwoods Village Parkway

Spring TX 77389

1-800-ASK MOBIL (275-6624)

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entity.



© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved