



Mobil DTE™ 800 Series

Mobil Industrial , United States

Superior Performance Turbine Oils

Product Description

Mobil DTE™ 832 and 846 are superior performance turbine oils designed for use in steam turbines, gas turbines and combined cycle gas turbine (CCGT) applications under the most severe operating conditions. These progressive products are based on high quality hydrotreated basestocks for exceptional thermal/oxidation resistance along with specially chosen additives engineered to provide the deposit control and "keep-clean" performance required by severe duty gas turbines as well as excellent water separability needed for steam turbine operation. The formulations also include a non-zinc antiwear system to meet the load carrying requirements of gas turbines.

In addition to meeting the separate requirements of modern steam and gas turbine designs, Mobil DTE 800 Series are excellent choices for combined cycle applications that require a single oil for a gas turbine and a steam turbine run in tandem. Simultaneously meeting both deposit control and water separation requirements is a performance highlight of this advanced lubricant technology. The excellent thermal/oxidative resistance of Mobil DTE 832 and 846 ensures that they can be operated in the most severe turbine environments.

The performance features of Mobil DTE 800 Series oils translate into excellent equipment protection, reliable operation, with reduced down-time and extended oil charge life. These products also provide the ultimate flexibility to the operator because they can be used in all turbine types: steam, gas and geared-turbines.

Features and Benefits

Mobil DTE brand mineral-based products have been the choice for turbine operators worldwide for more than one hundred years. During that period our company scientists have maintained the strongest ties with turbine equipment builders and operators to ensure that the needs of new turbine designs are met or exceeded by our lubricants. This has required a continual upgrading of Mobil turbine oils and the application of the most appropriate modern base oil and additive technology.

For modern stationary gas turbines that operate at high power outputs, exceptional protection against thermal/oxidative degradation and deposit control are required. Severe operation causes thermal stressing of the lubricant that can result in filter plugging, servo valve deposits or short oil life. For modern steam turbines, a high level of oxidation resistance is required as well as good water separability in cases of steam leaks. For combined cycle operation, it is necessary for the lubricant to meet the needs of both turbine types.

DTE 800 Series oils offer the following features and potential benefits:

Features	Advantages and Potential Benefits
Meets or exceeds both gas turbine and steam turbine requirements of key builders	Avoids lube misapplication and costly change-out Reduces inventory costs
Excellent thermal/oxidation stability	Reduced downtime, more reliable operation Extended oil charge life; lower product costs
Excellent antiwear protection	Excellent protection for geared turbines (gas- and steam-), lower maintenance replacement costs Extended equipment protection and reduced replacement costs
Excellent demulsibility	Efficient system operation and reduced maintenance

Applications

Mobil DTE 832 and 846 are superior performance turbine oils designed for use in steam and gas turbine oil systems, direct- or gear-coupled and turbine speed changeover mechanisms. Specific applications include:

- Combined cycle (CCGT) electric power generation applications including those with a common circulation system for the steam turbine and gas turbine.
- Lubrication of steam turbine or gas turbine units used for electric power generation, natural gas pipeline transmission, process operations and cogeneration plants

Specifications and Approvals

This product has the following approvals:	832	846
GE Power (former Alstom Power) HTGD 90117	X	X
Siemens TLV 9013 04	X	X
Siemens TLV 9013 05	X	X

This product is recommended for use in applications requiring:	832	846
GE Power GEK 28143B	X	X

This product meets or exceeds the requirements of:	832	846
DIN 51515-1:2010-02	X	X
DIN 51515-2:2010-02	X	X
GE Power GEK 101941A	X	
GE Power GEK 107395A	X	
GE Power GEK 121608	X	
GE Power GEK 28143A	X	X
GE Power GEK 32568Q	X	
GE Power GEK 46506D	X	
JIS K-2213 Type 2	X	X
Siemens Industrial Turbo Machinery MAT 812101	X	
Siemens Industrial Turbo Machinery MAT 812102		X
Siemens Industrial Turbo Machinery MAT 812106	X	
Siemens Industrial Turbo Machinery MAT 812107		X
Siemens Industrial Turbo Machinery MAT 812108	X	
Siemens Industrial Turbo Machinery MAT 812109		X
Siemens Westinghouse PD-55125Z3	X	
Solar Turbines ES 9-224, Class II	X	X

Properties and Specifications

Property	832	846
Grade	ISO VG 32	ISO VG 46
Air Release Time, 50 C, min, ASTM D3427	4	4
Copper Strip Corrosion, 3 h, 100 C, Rating, ASTM D130	1A	1A
Emulsion, Time to 0 mL Emulsion, 54 C, min, ASTM D1401	15	15
FZG Scuffing, Fail Load Stage, A/8.3/90, ISO 14635-1	8	8
Flash Point, Cleveland Open Cup, °C, ASTM D92	224	244
Foam, Sequence I, Stability, ml, ASTM D892	0	0
Foam, Sequence I, Tendency, ml, ASTM D892	20	20
Foam, Sequence II, Stability, ml, ASTM D892	0	0
Foam, Sequence II, Tendency, ml, ASTM D892	20	20
Foam, Sequence III, Stability, ml, ASTM D892	0	0
Foam, Sequence III, Tendency, ml, ASTM D892	20	20
Kinematic Viscosity @ 100 C, mm ² /s, ASTM D445	5.4	6.2
Kinematic Viscosity @ 40 C, mm ² /s, ASTM D445	29.6	42.4
Pour Point, °C, ASTM D97	-30	-30
Rotating Pressure Vessel Oxidation Test, min, ASTM D2272	1200	1100
Rust Characteristics, Procedure A, ASTM D665	PASS	PASS
Rust Characteristics, Procedure B, ASTM D665	PASS	PASS
Specific Gravity, 15.6 C/15.6 C, ASTM D1298		0.87
Specific Gravity, 15.6 C/15.6 C, ASTM D4052	0.86	
Turbine Oil Stability Test, Life to 2.0 mg KOH/g, h, ASTM D943	10,000+	10,000+
Viscosity Index, ASTM D2270	110	106

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

02-2024

Exxon Mobil Corporation

22777 Springwoods Village Parkway
Spring TX 77389

1-800-ASK MOBIL (275-6624)

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliated entities.

