



## Mobil Avrex S Turbo 256

ExxonMobil Aviation , Guinea

Aircraft Type Gas Turbine Lubricant

### Product Description

Mobil Avrex S Turbo 256 gas turbine lubricant is a combination of a highly stable synthetic base fluid and a unique chemical additive package. The combination provides outstanding thermal and oxidative stability to resist deterioration and deposit formation in both the liquid and vapor phases, as well as excellent resistance to foaming.

The effective operating range of Mobil Avrex S Turbo 256 is between -54°C and 176°C (-65°F and 350°F). The pour point is below -60°C (-75°F). The product has a high specific heat in order to ensure good heat transfer from oil-cooled engine parts. In extensive laboratory testing and in-flight performance, Mobil Avrex S Turbo 256 exhibits excellent bulk oil stability at temperatures up to 176°C (350°F). The evaporation rate at these temperatures is low enough to prevent excessive loss of volume.

### Application

Mobil Avrex S Turbo 256 is recommended for aircraft gas turbine engines in commercial and military service, particularly where start-up temperatures are below -40°F. The product is approved against U.S. Military Specification MIL-PRF-7808, Grade 3, and by the following engine and accessory manufacturers:

#### Engine and Accessory Approvals

Approved in equipment specifying 3 centistokes, MIL-PRF-7808 (latest revision) lubricants. Mobil Avrex S Turbo 256 is compatible with other synthetic gas turbine lubricants meeting MIL-PRF-7808 or MIL-PRF-23699 Specifications. However, mixing with other products is not recommended because the blend would result in a loss of the performance characteristics of Mobil Avrex S Turbo 256. The product is compatible with all metals used in gas turbine construction, as well as with FVMQ (Viton A), H rubber (Buna N), and FVMQ rubber (fluorosilicone).

### Advantages

Uniquely suited for use when extreme low temperatures restrict the use of higher viscosity engine oils.

### Typical Properties

| Avrex S Turbo 256                   |           | MIL-PRF-7808 Grade 3 Requirements |
|-------------------------------------|-----------|-----------------------------------|
| Product Number                      | 49423-7   | -                                 |
| Viscosity                           |           |                                   |
| cSt at 100°C (212°F)                | 3.3       | 3.0 min                           |
| cSt at 40°C (104°F)                 | 13.3      | 11.0 min                          |
| cSt at -51°C (-60°F) after 3 hr     | 10,459    | 17,000 max                        |
| cSt at -51°C (-60°F) after 72 hr    | 10,495    | 17,000 max                        |
| Flash Point, °C (°F)                | 224 (435) | 210 (410) min                     |
| Fire Point, °C (°F)                 | 256 (493) | -                                 |
| Pour Point, °C (°F)                 | -60 (-75) | -                                 |
| Specific Gravity, 15/15°C (60/60°F) | 0.9634    | -                                 |
| TAN, mg KOH/g                       | 0.03      | 0.30 max                          |
| Evaporation Loss, %                 |           |                                   |
| 6.5 hr at 204°C (400°F)             | 19.6      | 30 max                            |
| Foam, volume/collapse time          |           |                                   |
| Static, ml/sec                      | 20/6      | 100/60 max                        |
| Dynamic, ml/sec                     | pass      | 100/60 max                        |
| Rubber Swell, %                     |           |                                   |
| H Rubber, 168 hr at 70°C (158°F)    | 28.6      | 12-35                             |

| Avrex S Turbo 256                 |      | MIL-PRF-7808 Grade 3 Requirements |
|-----------------------------------|------|-----------------------------------|
| F Rubber, 72 hr at 175°C (347°F)  | 19.1 | 2-25                              |
| FS Rubber, 72 hr at 150°C (302°F) | 10.6 | 2-25                              |

## Health and Safety

Based on available information, this product is not expected to produce adverse effects on health when used for the intended application and therecommended provided in the Material Safety Data Sheet (MSDS) are followed. MSDS's are available upon request through your sales contract office, or via the Internet. This product should not be used for purposes other than its intended use. If disposing of used product, take care to protect the environment.

The ExxonMobil logotype, Mobil and Avrex S Turbo are trademarks of Exxon Mobil Corporation, or one of its subsidiaries. PDSAV-13

05-2020

Exxon Mobil Corporation  
22777 Springwoods Village Parkway  
Spring TX 77389

For additional technical information or to identify the nearest U.S. ExxonMobil supply source, call +1 800 662-4525.  
<http://www.exxonmobil.com>

Due to continual product research and development, the information contained herein is subject to change without notification. Typical Properties may vary slightly

**ExxonMobil**

Exxon Mobil ESSO XTO

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved