



Prowaxx™ 1475 SW

ExxonMobil specialties, Japan

产品介绍

Prowaxx 1475 SW 是 ExxonMobil Prowaxx 系列石蜡中的一种高熔点疏松蜡 [SW]。该产品在固体状态下为半透明结晶物质, 熔化后为黄色透明液体。我们利用精密控制的精炼工艺从石油中提取该物质, 其主要成分为直链正构烷烃和支链异构烷烃的混合物。

本产品按照埃克森美孚产品质量管理体系 EN ISO 9000 或同等标准进行生产和控制。

应用范围

在遵守各司法管辖区适用法律法规的前提下, Prowaxx™ 1475 SW 可用于以下用途*:

- 屋顶颗粒、道路、肥料、玻璃棉和纺织品处理的除尘
- 石蜡乳液
- 石蜡混合物
- 木材和纤维板施胶剂

*用户必须查证所作用途是否符合适用法规。

特性与规范

特性	标准方法 (a)	最小值	最大值
由自动三激比色计测出的 ASTM 颜色	ASTM D6045		2.0
100°C 时的运动黏度, mm ² /s	ASTM D445	6.8	8.5
含油量, wt%	ASTM D721		15.0
正构烷烃含量, 以%报告	ASTM D5442 mod	25	
闪点, 克利夫兰开口杯法测定, °C (F)	ASTM D92	232(450)	
凝固点, °C (F)	ASTM D938	60.0(140)	67.8(154)

注释 1: 我们的产品发布时已经过认证, 能够达到指定值。实际值可能会在指定测试方法的既定重现性范围内出现偏差。

注释 2: 为确保符合规范, 观察值或计算值应四舍五入到最后一个有效数字中最接近的单位, 以表示根据 ASTM E29 方法测定的极限值

(a) 如要替换标准测试方法, 您可以使用可替代的测试方法来认证产品属性。

健康与安全

有关本产品的健康与安全建议, 请参阅化学品安全技术说明书 (MSDS), 可于以下网站获取: <http://www.msds.exxonmobil.com/psims/psims.aspx>

除另行说明外, 此处所使用的所有商标均为埃克森美孚公司或其某一关联公司的商标或注册商标。

02-2024

ExxonMobil Asia Pacific Ltd

1 HarbourFront Place

#06-00 HarbourFront Tower One

Singapore 098633

+65 6885 5000

<http://www.exxonmobil.com>

Every care has been taken in the preparation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

ExxonMobil

Exxon

Mobil



© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved