Mobil™ Flush 320 Page 1 of 2



Mobil™ Flush 320

Mobil Industrial, Austria

Wind Turbine Gear Flushing Oil

Product Description

Mobil Flush 320 is a low-cost wind turbine gear flushing oil specifically designed for flushing / removing contaminants and ensuring long term performance of Mob Gear 320 WT during the oil change process - no matter the incumbent wind turbine gear oil in use.

Features and Benefits

- · Low-cost solution for flushing compared to a sacrificial Mobil SHC Gear 320 WT flushing charge
- Removes residual oil and contaminants from wind turbine gearbox systems to ensures optimum "new oil" performance of Mobil SHC Gear 320 WT
- Optimized ISO 320 viscosity to avoid compromising viscosity of final charge and ensure adequate wear protection
- No foaming and filter blocking to ensure trouble free operations
- Comes with low Sulphur formulation to avoid potential risk of "Sulphur syndrome"
- No impact to oxidation resistance on the incoming oil charge even with higher than expected flush oil carry over

Applications

Mobil Flush 320 can be used as a flushing oil for wind turbine gearbox systems when the intention is to change any incumbent wind turbine gear oil to Mobil SHC^T 320 WT.

Mobil Flush 320 can be used as a flushing oil for wind turbine gearbox systems to remove contaminants from an in-service gearbox or as a flushing oil duri installation or repair of a wind turbine gearbox.

Mobil Flush 320 is not designed to be a long-term gear oil replacement. It is meant to be used only as a flushing gear oil.

Even if compatibility between the incumbent oil and Mobil SHC™ Gear 320 WT has been deemed acceptable, it is highly recommended to flush the wind turbine g system to ensure optimum performance. In case of incompatibility, flushing is mandatory.

In order to ensure Mobil SHC[™] Gear 320 WT performance is optimized and its 10-year warranty is not impaired, a thorough changeover procedure should be foll Essential steps are as follows:

- Drain the incumbent oil
- Clean the inside oil system including filter housing and oil cooler
- Change out filters, fill with Mobil Flush 320 up to 60% of the oil system capacity
- Run the wind turbine unloaded at high speed for 1-2 hours while oil temperature is ~60°C. Filter plugging must be closely monitored.
- Drain the Mobil Flush 320 charge as thoroughly as possible and repeat previous 2 steps if deposits or contaminants are still visible.
- \blacksquare Fill with the final Mobil SHC[™] Gear 320 WT charge

For the detailed conversion protocol: visit Tech Topic "Wind Turbine Gear Oil Conversion Protocol".

The used Mobil Flush 320 charge may be reused for another wind turbine gearbox if cleanliness level is acceptable.

ExxonMobil has an extensive database of compatibility studies with competitive products, change out protocols, and other resources in order to support our cust with oil change outs.

Mobil™ Flush 320 Page 2 of 2

Properties and Specifications

Property	
Grade	ISO 320
Kinematic Viscosity @ 100 C, mm2/s, ASTM D445	29.6
Pour Point, °C, ASTM D5950	-30
Flash Point, Cleveland Open Cup, °C, ASTM D92	272
Density @ 15.6 C, g/ml, ASTM D4052	0.873
Phosphorus, mass%, ASTM D4951	390
Kinematic Viscosity @ 40 C, mm2/s, ASTM D445	335
Viscosity Index, ASTM D2270	121

Health and safety

 $Health\ and\ Safety\ recommendations\ for\ this\ product\ can\ be\ found\ on\ the\ Material\ Safety\ Data\ Sheet\ (MSDS)\ @\ http://www.msds.exxonmobil.com/psims/psims.as$

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

12-2023

ExxonMobil Lubricants & Specialties Europe, division of ExxonMobil Petroleum & Chemicals BVBA.

This information relates only to products supplied in Europe (including Turkey) and the Former Soviet Union.

EXXONMOBIL LUBRICANTS & SPECIALTIES EUROPE, A DIVISION OF EXXONMOBIL PETROLEUM & CHEMICAL, BVBA (EMPC)

POLDERDIJKWEG

B-2030 Antwerpen

Belgium

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All promay not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

