



Mobil Pyrotec™ HFD 46B

Mobil Industrial , Switzerland

Fire-Resistant Hydraulic Fluid

Product Description

Mobil Pyrotec™ HFD 46B is a high performance phosphate ester self-extinguishing fire resistant hydraulic fluid. Mobil Pyrotec HFD 46B is TXP-free.

Mobil Pyrotec HFD 46B has been evaluated in stringent tests for fire resistance such as the ISO 20823 manifold ignition test. Compared to other types of synth mineral fire resistant fluids, Mobil Pyrotec HFD 46B shows a much higher ignition temperature (greater than 700°C) and is very difficult to ignite. If ignited, the flar self-extinguish.

Mobil Pyrotec HFD 46B is formulated from specially purified phosphate base stocks and additives providing improved oxidation stability and lubrication prop Physical properties such as foaming, air release and demulsibility are controlled to meet the limits specified by turbine manufacturers.

Features and Benefits

Features	Advantages and Potential Benefits
High ignition temperature and self-extinguishing capability, approved by FM Approvals	Preferred choice in applications where fire safety is critical
TXP-free formulation	Compliance with future safety, health and environment regulations
Excellent oxidation resistance	Helps to extend oil life
Excellent anti-wear properties	Helps to extend component life

Applications

Mobil Pyrotec HFD 46B is recommended for use in applications where fire safety is critical, such as:

- Electro-hydraulic governor control systems of steam turbines, especially where a high performance fluid is required,
- Hydraulic and oil circulation systems operating in conditions subject to fire hazards,
- Other applications such as gas turbines, turbo-compressors, reactor coolant pumps and generators.

Please note that Mobil Pyrotec HFD 46B is fully compatible with Mobil Pyrotec HFD 46.

Special precautions should be taken when using Mobil Pyrotec HFD 46B regarding:

- System operating temperatures: normal system temperature should be between 50 and 65°C to avoid water condensation and local spot temperatures sho kept below 150°C,
- Flushing procedure when replacing petroleum oils, conventional soluble emulsions, water in oil emulsions or water glycol fluids,
- Compatibility with elastomers (for example, Mobil Pyrotec HFD 46B is not recommended for use with Neoprene, nitrile and silicon materials but compatibl seals and hose materials such as butyl rubber and Viton),
- Compatibility with paints, enamels and varnishes (for example, Mobil Pyrotec HFD 46B is not recommended for acrylic, latex and phenolic resin pair compatible for example with epoxy type paints).

Please contact your your ExxonMobil representative for further details.

## Specifications and Approvals

**This product has the following approvals:**

FM Global Approvals Class 6930

Siemens TLV 9012 02

Siemens TLV 9012 03

Mitsubishi Power Ltd MS04-MA-CL004(Rev.6)

**This product meets or exceeds the requirements of:**

GE Power GEK 46357H

## Properties and Specifications

Property	
Grade	ISO 46
Kinematic Viscosity @ 40C, mm2/s, ISO 3104	43.5
Flash Point, Cleveland Open Cup, °C, ISO 2592	258
Foam Sequence II, Tendency, ml, ISO6247	15
Foam Sequence II, Stability, ml, ISO6247	0
Water Separability, min, ISO 6614	5
Total Acid Number, mgKOH/g, ISO 6619	0.04
Volume Resistivity 20C, MOhm.m, IEC 60247	340
Water, wt %, ISO 760	0.06
Chlorine, ppm, IP 510/04	5
Appearance, Visual	Clear
Particle Count, Rating, ISO 4406	-/15/12 (max)

## Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

04-2022

EXXONMOBIL LUBRICANTS & SPECIALTIES EUROPE, A DIVISION OF EXXONMOBIL PETROLEUM & CHEMICAL, BVBA (EMPC)

POLDERDIJKWEG

B-2030 Antwerpen

Belgium

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All properties may not be available locally. For more information, contact your local ExxonMobil contact or visit [www.exxonmobil.com](http://www.exxonmobil.com)

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entity.

