



WYROL B

Mobil Industrial , Switzerland

Bearing Oil

Product Description

WYROL B Series are low staining bearing oils designed for use in aluminium cold rolling mills. They are formulated using select mineral base oils, a polymeric thickener and performance enhancing additives. If conventional oils contaminate aluminium roll oils as a result of leakage, staining problems are sometimes experienced on the finished aluminium after annealing. WYROL B oils reduce this problem, as the oil is removed from the aluminium piece during the annealing process. They have good anti-wear characteristics and protect heavily loaded bearings from damage and wear. WYROL B oils also exhibit good oxidation stability and corrosion prevention properties. Wyrol B conforms to FDA Regulation FDA 21 CFR 178.3570 "Lubricants with incidental food contact". They therefore can be used as bearing fluids in aluminium rolling mills, which produce products such as foil for use as food packaging materials.

Features and Benefits

WYROL B oils are specifically designed to overcome the problems generated when conventional bearing lubricating oils contaminate the roll oils and result in finished product staining. They also provide very good lubrication characteristics to reduce wear and provide long service life.

WYROL B oils offer the following benefits:

- Very low staining properties improve the production of acceptable materials
- Reduced manpower costs for clean-up and lower scrapage rates
- Good anti-wear characteristics increase bearing life
- High oxidation stability increases oil service life

Applications

The leakage of aluminium roll oil into the bearing system results in the reduction of viscosity of the bearing oil. In such cases, WYROL B 2200, a special concentrate, may be used to adjust the viscosity of the roll oil-contaminated bearing oil to the required level.

- Bearing lubrication in aluminium rolling applications
- They are suitable for bath or mist lubrication systems

Specifications and Approvals

This product meets or exceeds the requirements of:	460
FDA 21 CFR 178.3570	X

Properties and Specifications

Property	460
Grade	ISO 460
Ash, Petroleum Products, mass%, ISO 6245	
Flash Point, °C, ASTM D93	

Property	460
Flash Point, Pensky-Martens Closed Cup, °C, ASTM D93	Min 130
Kinematic Viscosity @ 40 C, mm ² /s, ASTM D445	460
Neutralization Number, mgKOH/g, ASTM D974	Max 0.8
Pour Point, °C, ASTM D97	Max -12
Viscosity Index, ASTM D2270	160

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

10-2024

EXXONMOBIL LUBRICANTS & SPECIALTIES EUROPE, A DIVISION OF EXXONMOBIL PETROLEUM & CHEMICAL, BVBA (EMPC)

POLDERDIJKWEG

B-2030 Antwerpen

Belgium

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

ExxonMobil



© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved