Mobilect™ 36 Page 1 of 2



### Mobilect™ 36

Mobil Industrial, Chile

Electrical insulating oils

### **Product Description**

Mobilect™ 36 is a mineral uninhibited insulating oil with dielectric properties and oxidation stability intended for transformers, switchgears and other ele equipment. Mobilect 36 meets ASTM D3487, Type I.

#### Features and Benefits

Mobilect has resistance to thermal and chemical degradation in the presence of iron and copper, which reduces tendencies to produce sludge

and oil-soluble oxidation products. When lower quality oils are used these may form deposits in the transformer and impede heat transfer by interfering with conv currents. In addition deposits may accelerate insulation defects and are often very difficult to remove without complete dismantling.

- The dielectric strength of Mobilect is a measure of the resistance of the oil to electric stress and is expressed in kV across a specified gap under test conditions. not a measure of the quality of the oil but of the absence of contaminants especially moisture, fibres and polar chemicals.
- Mobilect is free from wax even at low temperatures and thus circulates freely in outdoor applications. Its viscosity ensures readily heat transfer by mobile convcurrents. Mobility is also essential to quick quenching of arcs in switchgear units.
- The low pour point of Mobilect ensures a free flow in most conditions between the transformer and the conservator and maintains the reliability of tap changers lowest temperatures.

## **Applications**

Mobilect is recommended for use in oil filled transformers and witch gears in which the oil is required as an insulation medium or as a heat transfer medium.

## Specifications and Approvals

This product meets or exceeds the requirements of:
ASTM D3487, Type I

# **Properties and Specifications**

Property	
Interfacial Tension, 25 C, mN/m, ASTM D971	50
Flash Point, Cleveland Open Cup, °C, ASTM D92	150
Oxidation Stability @ 164 hr - Acid Number C, mgKOH/g, ASTM D2440	0.1
Breakdown Voltage, kV, ASTM D877	55
Density @ 15 C, kg/l, ASTM D4052	0.89
Pour Point, °C, ASTM D97	-60
Kinematic Viscosity @ 40 C, mm2/s, ASTM D445	9

## Health and safety

Mobilect™ 36 Page 2 of 2

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

04-2023

COPEC S.A.

Isidora Goyenechea 2915, Las Condes, Santiago Chile

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All promay not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

