



Mobil SHC PF 462

Mobil Industrial , Chile

High Temperature Grease

Product Description

Formulated with perfluoropolyether that has been thickened with polytetrafluoroethylene, Mobil SHC PF 462 is a long-life, severe-service grease for bearings, valves, seals and other applications that require oxidation stability and lubrication performance at high temperatures.

Features and Benefits

Mobil SHC PF 462 provides dependable performance up to 240 °C (464 °F). Mobil SHC PF 462 provides excellent lubricity, corrosion resistance, thermal and oxidative stability and chemical inertness.

Mobil SHC PF 462 is non-flammable and highly resistant to oxidative degradation at temperatures up to 240 °C (464 °F). The high-temperature stability provides bottom line savings from improved reliability and reduction in grease usage and manpower through extended re-lubrication intervals.

Mobil SHC PF 462 is resistant to attack by chemicals and contaminants, including hydrocarbon oils, alcohols, acids, and caustic.

- Superb High-Temperature Stability
- Dependable performance at high temperatures
- Resistance to chemicals, caustics and solvents *

* Testing should be conducted to verify resistance before use in intended service. Not intended for pressurized oxygen service without testing and validation by the equipment builder and intended operator.

Applications

Mobil SHC PF 462 is engineered to provide excellent performance for a wide variety of demanding high-temperature applications including those found in the textile, steel, aluminum rolling, automotive, aerospace and forest product industries.

Mobil SHC PF 462 is compatible with other PFPE/PTFE greases, but should not be used with typical mineral or synthetic greases.

Properties and Specifications

Property	
Grade	NLGI 2
Base Oil Viscosity of Greases @ 100 C, mm ² /s, AMS 1697	42
Base Oil Viscosity of Greases @ 40 C, mm ² /s, AMS 1697	440
Color, Visual	White
Copper Strip Corrosion, Rating, ASTM D4048	1B
Corrosion, Bearing, Rating, ASTM D1743	PASS
Dropping Point, °C, ASTM D2265	258
Flash Point, Base Oil, °C, ASTM D92	Does not ignite

Property	
Four-Ball Extreme Pressure Test, Weld Point, kgf, ASTM D2596	800 Pass
Four-Ball Wear Test, Scar Diameter, mm, ASTM D2266	0.58
High-Temperature Wheel Bearing Test, Leakage, g, ASTM D4290	0.5
Oil Separation, mass%, ASTM D1742	1.08
Oxidation Induction Time(PDSC), Minutes to Induction, 210 C, minutes, ASTM D5483	No Induction
Roll Stability, 0.1 mm, ASTM D1831	2.7
SKF Emcor Rust Test, Distilled Water, ASTM D6138	0,0
US Mobility @ 0F, g/min, AMS 1390	7.4
Water Sprayoff, Loss, %, ASTM D4049	5
Water Washout, Loss @ 79 C, wt%, ASTM D1264	0.94

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

02-2024
COPEC S.A.

Isidora Goyenechea 2915, Las Condes, Santiago Chile

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

ExxonMobil

Exxon

Mobil

Esso

XTO
ENERGY

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved