



Spartan™ EP 680

Mobil Commercial Vehicle Lube , Colombia

Gear Oil

Product Description

Spartan™ EP 680 is part of Spartan EP Series, a family of industrial extreme pressure gear lubricants. They are formulated with high quality mineral oils, which reduce sludge formation helping to increase oil service life. Spartan EP oils contain a sulphur / phosphorus extreme pressure additive system that gives high load capacity and protection against wear. In addition these oils provide strong protection against corrosion of steel and copper containing alloys and resist foaming. Spartan oils have good water handling properties so that water rapidly separates from the oil for easy water elimination.

Spartan EP oils can be used in either splash or circulating systems. Spartan EP gear oils are suitable for use wherever industrial gear oil is required. Spartan EP gear oil is suitable for the lubrication of heavily loaded enclosed gear sets including spur, helical and bevel designs and provide protection in applications where shock loads occur. Spartan EP may also be used in worm gears where specified. They may also be used for lubrication of plain bearings, and in rolling contact (anti-friction) bearings.

Features and Benefits

Spartan EP gear oils offer the following benefits:

Spartan EP oils enjoy a reputation for quality and consistency, as well as the ability to handle a variety of tough gear applications. They are manufactured with high quality mineral stocks and a specially chosen additive system. Spartan EP lubricants are manufactured under the highest level of quality assurance and control in our modern blending facilities.

- EP wear protection of gears and bearings
- Resistance to sludge formation leads to outstanding system cleanliness
- Very good oxidation resistance for long oil change life
- Very good demulsibility to ease water removal

Applications

Spartan EP gear oils are used in a wide range of industrial spur, helical, bevel and steel-on-steel worm gearing.

Properties and Specifications

Property	
Grade	ISO 680
Density @ 15.6 C, kg/l, ASTM D4052	0.914
Kinematic Viscosity @ 100 C, mm2/s, ASTM D445	36.4
Pour Point, °C, ASTM D97	-6
Emulsion, Time to 37 mL Water, 82 C, min, ASTM D1401	40
FZG Scuffing, A/8.3/90, Fail Stage, Rating, DIN 51354	12+
Viscosity Index, ASTM D2270	87
EP Properties, Timken OK Load, lb, ASTM D2782	55

Property	
Copper Strip Corrosion, 3 h, 100 C, Rating, ASTM D130	1B
Four-Ball Extreme Pressure Test, Weld Load, kgf, ASTM D2783	190
Four-Ball Extreme Pressure Test, Load Wear Index, kgf, ASTM D2783	45
Kinematic Viscosity @ 40 C, mm2/s, ASTM D445	680
Rust Characteristics, Procedure B, ASTM D665	Pass

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

04-2021

Organización Terpel S.A.

Address: Carrera 7 N° 75-51, Bogotá – Colombia

Phone: (57) 1 3267878

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All properties may not be available locally. For more information, contact your local ExxonMobil contact or visit [www.exxonmobil.com](http://www.exxonmobil.com)

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entity.

ExxonMobil

Exxon

Mobil

Esso

XTD

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved