



## Mobil Polyrex 461 EP

Mobil Grease , France

High temperature multi-purpose grease

### Product Description

Mobil Polyrex™461 EP is a shear-stable polyurea grease with excellent extreme-pressure (EP) and load-carrying characteristics. The proprietary polyurea thickener system exhibits excellent resistance to oxidation and oil separation at operating temperatures as high as 170°C. With its outstanding high-temperature oxidation stability, load-carrying capability, shear stability, water resistance and wide operating temperature range, Mobil Polyrex™461 EP is an excellent multi-purpose grease for a wide array of industrial applications such as steel mills and wood pellet machines. This grease has excellent pumpability in central grease systems. Recommended operating temperature range is from -20 °C to 170 °C.

Mobil Polyrex™461 EP meets the claim by DIN KPF1P-20.

### Features and Benefits

#### EXTREME-PRESSURE PROTECTION AND THERMAL STABILITY

Mobil Polyrex™461 EP contains a proprietary extreme-pressure package with solid additives that provides load-carrying capability without degrading the thermal stability of the grease at high temperatures. This grease can provide a high level of wear and extreme-pressure protection up to 170°C without rapid oxidation of the anti-wear or EP additives. Very good anti-oxidation protection imparted by the advanced polyurea thickener.

#### EXCELLENT PUMPABILITY IN CENTRALIZED GREASE SYSTEMS

Due to consistency grade NLGI 1 this grease is suitable for long distribution systems with very good mobility down to 0°C. Grease can allow to stretch performance to -20°C depending on central system design.

#### GOOD WATER PROTECTION

Mobil Polyrex™461 EP provides an effective water resistance to keep grease in place. Corrosion prevention protects bearings in presence of water

### Applications

Suitable for medium to slow speed moving plain or roller bearings exposed to high temperatures, severe load and shock loading in the following industrial applications:

Steel mill continuous casters & roll mills

Wood pellet mills

Cement, Glass, Mining, Chemical plants equipment

### Specifications and Approvals

<b>This product meets or exceeds the requirements of:</b>
DIN 51825:2004-06 - KPF 1 P -20

### Properties and Specifications

Property	
Grade	NLGI 1

Property	
Copper Strip Corrosion, Rating, ASTM D4048	1B
Rust, Rating, ASTM D1743	Pass
SKF Emcor Rust Test, Distilled Water, ASTM D6138	0-1
Four-Ball Extreme Pressure Test, Weld Load, kgf, ASTM D2596	400
Four-Ball Wear Test, Scar Diameter, mm, ASTM D2266	0.5
Flow Pressure at -20C, mbar, DIN 51805	900
Water Washout, Loss @ 79 C, wt%, ASTM D1264	1
Base Oil Viscosity of Greases @ 40 C, mm <sup>2</sup> /s, AMS 1697	460
Color, Visual	Green
Texture, VISUAL	Smooth and Tacky
Dropping Point, °C, ASTM D2265	255
Penetration, 60X, 0.1 mm, ASTM D217	325

## Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

05-2020

### Esso Société Anonyme Française

20 rue Paul Héroult  
92000 Nanterre, France

Société Anonyme au capital de 98 337 521,70 euros

RCS Nanterre 542 010 053

You can always contact our Technical Help Desk engineers on Mobil lubricants and services related questions: <https://www.mobil.fr/fr-fr/contact-us>

Tel. +33 (0)1 49 67 90 00

<http://www.exxonmobil.com>

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit [www.exxonmobil.com](http://www.exxonmobil.com)

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

Energy lives here™

**ExxonMobil**



© Copyright 2003-2022 Exxon Mobil Corporation. All  
Rights Reserved