Mobilarma™ 778 Page 1 of 2



Mobilarma™ 778

Mobil Industrial, France

Premium Performance Rust Preventives

Product Description

The Mobilarma 778 is intended for protection cold-rolled sheet and coiled steel in the metal industry and it exhibit excellent water displacing properties and for tenacious films that protect surfaces even under severe conditions that include high moisture levels and exposure to acid or corrosive fumes.

The Mobilarma 778 forms wet, oily and extremely thin barrier films that are not tacky so that it will not attract dirt or other foreign matter. It will protect sheet and steel for up to twelve months, even under severe conditions that include variations in humidity and exposure to acid fumes that might be found in the vicinity of p operations.

Features and Benefits

Mobilarma 778 provides an effective and cost efficient means of protecting cold-rolled sheet and coiled steel prior to processing and during storage. It provides ext protection, even under severe storage conditions resulting in less reject and scrapped materials.

Features	Advantages and Potential Benefits
Effective rust and corrosion protection	
	Less waste and lower costs
Easy application	
	Less waste and lower costs
Economical to use	
	Good coverage and protection with thin films

Applications

Mobilarma 778 is recommended for use as:

- Protective coatings for cold-rolled sheet and coiled steel
- Coatings for precision machined parts and instruments for storage
- A die lubricant in some light duty pressing operation

Properties and Specifications

Property	
Flash Point, Cleveland Open Cup, °C, ASTM D92	226
Density @ 15 C, g/cm3, ASTM D4052	0.877
Kinematic Viscosity @ 40 C, mm2/s, ASTM D445	38.9

Mobilarma™ 778 Page 2 of 2

Property	
Pour Point, °C, ASTM D97	-12

Health and safety

 $Health\ and\ Safety\ recommendations\ for\ this\ product\ can\ be\ found\ on\ the\ Material\ Safety\ Data\ Sheet\ (MSDS)\ @\ http://www.msds.exxonmobil.com/psims/psims.as$

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

06-2023

Esso Société Anonyme Française

20 rue Paul Héroult

92000 Nanterre, France

Société Anonyme au capital de 98 337 521,70 euros

RCS Nanterre 542 010 053

You can always contact our Technical Help Desk engineers on Mobil lubricants and services related questions: https://www.mobil.fr/fr-fr/contact-us Tel. +33 (0)1 49 67 90 00

http://www.exxonmobil.com

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All promany not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

