



WALZOEL BM 71/W27

Mobil Industrial , France
Rolling Oils

Product Description

Walzoel W-27 is a fully formulated aluminium rolling oil based on a high quality mineral oil cut with specially selected non staining additives, which permit re lubrication characteristics to be obtained.

Walzoel BM 71 is a copper and copper alloys rolling oil that consists of high quality base oils and carefully selected additives to enhance lubricity and oxidation stabi

Features and Benefits

Walzoel W-27:

- Meets US FDA Regulation 21 CFR 178.3910, Surface Lubricants Used in Manufacture of Metallic Articles
- Clean annealing properties reduce potential for production rejections.
- Compliance with FDA regulation allows use in production of food packaging material.
- Extremely low aromatics content and low odor makes the roll oil acceptable to workers and the environment.
- Reduced evaporation due to the extremely narrow boiling range of the base oil.

Walzoel BM 71:

- Excellent filterability characteristics in filter systems using active and/or inactive earth. Additive depletion is low in systems, where only inactive earth is used. Ent filterability allows clean rolling oil in service.
- No sulphur-containing additives.
- Very low additive depletion rate.

Applications

Walzoel W-27:

Walzoel W-27 is particularly suited for rolling aluminum sheet and strip. It provides clean annealing without the need of degreasing beforehand. The additives u Walzoel W27 provide good reduction capability for aluminum alloys. For additive top-up the corresponding additive package Wyrol 8 is available.

Walzoel BM 71:

Walzoel BM 71 is particular suited for rolling of copper and copper alloys on four-high and six-high mills where roll bearings are not lubricated by the rolling oil. TI viscosity provides excellent cooling properties. The very good oxidation resistance and the absence of acidic components prevent the formation of dissolved c soaps.

Properties and Specifications

Property	W-27	BM 71
Appearance, AMS 1738	Clear and Bright	Clear and Bright
Density @ 15 C, kg/m3, ASTM D4052	817.5	849.5
Kinematic Viscosity @ 20 C, mm2/s, ASTM D445	3	
Kinematic Viscosity @ 40 C, mm2/s, ASTM D445		7.2

Property	W-27	BM 71
Neutralization Number, mgKOH/g, ASTM D974	<0.05	<0.1
Pour Point, °C, ASTM D97	<-3	<-18

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

03-2021

Esso Société Anonyme Française

20 rue Paul Héroult
92000 Nanterre, France

Société Anonyme au capital de 98 337 521,70 euros

RCS Nanterre 542 010 053

You can always contact our Technical Help Desk engineers on Mobil lubricants and services related questions: <https://www.mobil.fr/fr-fr/contact-us>

Tel. +33 (0)1 49 67 90 00

<http://www.exxonmobil.com>

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product perfor are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All pr may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is inten override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

ExxonMobil

Exxon

Mobil

Esso

XTD

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved