# **Mobil**<sup>®</sup>

# Mobil SHC™ Chain 240

Mobil Industrial , Kazakhstan

High Temperature Chain Lubricant

# Product Description

Mobil SHC Chain 240 is an exceptional performance chain lubricant designed for lubrication of high temperature conveyor chains at temperatures up to 290°C / 5! is designed to provide excellent wear protection and resistance to evaporation, thermo-oxidation and coking.

## Features and Benefits

Mobil SHC Chain 240 helps to:

- · Provide a degree of equipment protection beyond the capabilities of conventional chain lubricants
- Provide extra reassurance of trouble-free equipment protection at very high temperatures
- Extend equipment life, reduce costs, improve total system performance
- Prevent wear of chains, sprockets, and other system components
- Reduce deposit formation thereby reducing chain sticking
- Provide lasting lubrication of chains at high temperatures
- Reduce lubricant consumption compared to conventional chain lubricants

### Applications

Mobil SHC Chain 240 is designed specifically for the lubrication of oven conveyor chains at temperatures up to 290°C (555° F). It is suitable for high temperature applications in:

- Fiber glass insulation manufacture
- Particleboard (OSB , MSB) manufacture
- Plastics and textiles manufacture
- Paint oven operations

### **Properties and Specifications**

Property	
Copper Corrosion, 3 Hrs @ 100C, Rating, ISO 2160	1A
Density @ 20C, kg/m3, ISO 12185	968
Evaporation Loss, 6.5 h, 204 C, mass%, ASTM D972(mod)	1
Flash Point (COC), C, EN ISO 2592	290
Foam, Sequence I, Stability, 24 C, ml, ISO 6247	0
Foam, Sequence I, Tendency, 24 C, ml, ISO 6247	50
Four-Ball Extreme Pressure Test, Weld Load, kgf, ASTM D2783	160
Four-Ball Wear Test, Scar Diameter, 40 kg, 1200 rpm, 1 h, 75 C, mm, ASTM D4172	0.4
Kinematic Viscosity @ 100 C, mm2/s, ISO 3104	19

Property	
Kinematic Viscosity @ 40C, mm2/s, ISO 3104	245
Pour Point, °C, ISO 3016	-24
Viscosity Index, ISO 2909	86

#### Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

10-2021

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All primary not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

