



Somentor A Series

Mobil Industrial , North Macedonia

Fully Compounded Cold Rolling Oils

Product Description

Somentor AH 45, AH 70 and AL 70 are premium quality, fully compounded oils suitable for cold rolling of ferrous and non-ferrous metals. These oils are formulated with high quality base stocks and specially selected roll oil additives to meet the demanding performance requirements of these applications.

Features and Benefits

Somentor A Series oils are formulated to efficiently provide quality production of cold rolled parts made from steel or non-ferrous metals. Features and benefits include:

- Delivery of a bright surface finish on rolled metal
- Clean evaporation in the annealing process to prevent residues/deposits
- Easy filtration to extend the life of the oil
- Suitable for a wide range of metals
- Low viscosity of Somentor AH45 improves cooling efficiency and can be blended to cost effectively adjust the viscosity of AH 70 and AL 70 cold rolling oils.

Applications

Somentor A Series provide reliable and efficient lubrication and cooling during a wide variety of cold rolling applications.

- Suitable for a wide range of ferrous and non-ferrous metals, Somentor A series products can be used to cold roll high carbon, austenitic and ferritic stainless steel, as well as copper and copper alloys.
- Somentor A series is suitable for use on all mill configurations including 4 hi mills through to 20 hi multi-roll mills.
- Somentor A series products are suitable for the lubrication of back up bearings in multi-hi mills.
- Can be used in applications where filter systems employ active and/or inactive earth filter media.
- Somentor A series grades are suitable for use in rolling mill hydraulic systems to reduce contamination effects, depending on pump suitability for low viscosity oils.

Typical Properties

Somentor A			
Grad	AH 45	AH 70	AL 70
Appearance, visual	Clear and Bright	Clear and Bright	Clear and Bright
Kinematic Viscosity, ISO 3104			
mm ² /s @ 40°C	4.2	7.3	7.2
Pour Point, °C, ISO 3016	-6	-6	-6
Flash Point, °C, ISO 2592	140	152	160
Density @15 °C kg/l, ASTM D 4052	822	852	850
Neutralization Number, mgKOH/g, ISO 6618	<0.05	<0.1	<0.1

Health and Safety

Based on available information, this product is not expected to produce effects on health when used for the intended application and the recommendations provided in the Material Safety Data sheet (MSDS) are followed. MSDS's are available upon request through your sales contract office, or via the Internet on (insert Internet address). This product should not be used for purposes other than its intended use. If disposing of used product, take care to protect the environment.

The Mobil logotype, the Pegasus design, and Somentor are trademarks of ExxonMobil Corporation, or one of its subsidiaries.

06-2021

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

Energy lives here™

ExxonMobil

Exxon Mobil Esso XTO

© Copyright 2003-2019 Exxon Mobil Corporation. All Rights Reserved